

GRAVIHEL PUR SINGLE COAT 421 SEMI GLOSS (PUR SC - 421)

Use: Two-component single-layer coating with high weather and UV protection for long-term exposure. Used in the protection system for construction and agricultural machinery, rail vehicles, different steel constructions, and for industrial varnishing which requires a high level of mechanical, chemical and weather resistance. It is possible to use it on zink sheet plate, but it is obligatory to use GraviHEL 2K PUR single coat hardener - mixing ratio by volume 4:1.

The recommended ratio between the binder and the pastes is 80 : 20: If a superior hiding power is required, the quantity of pastes can be increased to a ratio of 75 : 25. All further information is provided based on the 80 : 20 ratio.

Type of product:

Acryl - isocyanate

Appearance:

Semi gloss

Delivery viscosity:

Thixotropic

Density of component A:

1,4 – 1,565 kg/l

Solid Content::

By volume: 45%

By weight : 76%

VOC:

2004/42/IIIB(e)(840)490

VOC ready to use (g/l)= max.490

Theoretical yield:4 - 5 m² /lit.**Color shades:**

GraviHEL Color Tools

Distributed by:

Crest Cormix Pty. Ltd.

13 Newmarket Lane,

Epping, Victoria 3076.

Tel: +61 3 9945 2700

Fax: +61 3 9945 2799

Email: enquiries@crestcormix.com.au

Web: www.crestcormix.com.au

HELIOS TBLUS, d.o.o., Količevo 65, 1230 Domžale, Slovenija

T: +386 1 722 40 00, E: info@helios.si, www.helios.si

**2:1 + 10-15%****GraviHEL 2K PUR hardener****GraviHEL thinner ESS**

Volume mixing

Pot life / 20°C = 4h




18 – 20 sec.

DIN 53211 Φ 4mm/ 20°C

1,3 – 1,7 mm

2 - 3 bar (depending on type of gun)

1 -2x = 80 -120 μ m

Between coats: 10 min. /20°C



Powder dry/20°C =30 minutes

Dry to touch/20°C = 5 h

60°C = 30 minutes



8 – 12 min. in the short-wave



0 - 10%


GraviHEL thinner ESS

0,23 – 0,33 mm

80 – 200 bar



Thinner is not needed!



Shelf life:

2 years

