

GRAVIHEL ALKYD TOPCOAT 201 GLOSS (A - 201)

Use: : One-component, quick-drying top coating for the protection of agricultural and construction machinery, rail vehicles, and for industrial varnishing of other steel surfaces which requires quick drying. The recommended ratio between the binder and the pastes is 85 : 15. If a superior hiding power is required, the quantity of pastes can be increased to a ratio of 80 : 20. All further information is provided based on the 85 : 15 ratio.

Surface:

GraviHEL alkyd primer RAL

Type of product:

Alkyd

Appearance:

gloss

Delivery viscosity:

DIN4 /20°C = 145 – 150 sec.

Density of component A:

1,087 – 1,193 kg/l

Solid Content:**By volume:** 26%**By weight:** 59%**VOC:**

VOC ready to use (g/l)= max.570

Theoretical yield:6 - 7 m²/lit.**Color shades:**

GraviHEL Color Tools



10-15%


GraviHEL 1K thinner

26 – 28 sec.

DIN 53211 ϕ 4 /20°C

1,3 mm

2 - 3 bar (depending on type of gun)

2x = 40 μ m

Between coats: 5-10 min. /20°C



Powder dry/20°C= 10 minutes

Dry to touch/20°C = 1h

5 - 10% **GraviHEL 1K thinner**

0,23 – 0,33 mm

120– 150 bar

**GraviHEL alkyd topcoat 201 gloss****+ GraviHEL 1K matting agent**

10% = semi gloss

30% = mat



Shelf life:

2 years

Distributed by:

Crest Cormix Pty. Ltd.

13 Newmarket Lane,

Epping, Victoria 3076.

Tel: +61 3 9945 2700

Fax: +61 3 9945 2799

Email: enquiries@crestcormix.com.auWeb: www.crestcormix.com.au