

Technical information (7/2016)

GRAVIHEL PUR SINGLE COAT 420 HIGH GLOSS (PUR SC - 420)



Use: Two-component single-layer coating with high weather and UV protection for long-term exposure. Used in the protection system for construction and agricultural machinery, rail vehicles, different steel constructions, and for industrial varnishing which requires a high level of mechanical, chemical and weather resistance. It is possible to use it on zink sheet plate, but it is obligatory to use GraviHEL 2K PUR single coat hardener - mixing ratio by volume 4:1.

The recommended ratio between the binder and the pastes is 80 : 20: If a superior hiding power is required, the quantity of pastes can be increased to a ratio of 75 : 25. All further information is provided based on the 80 : 20 ratio.

Type of product: Acryl - isocianate

Appearance: High gloss

Delivery viscosity: DIN4 /20°C = 140 - 170s

Density of component A: 1,325 - 1,483 kg/l

Solid Content: By volume: 47% By weight: 89%

VOC: 2004/42/IIB(d)(420)300 VOC ready to use (g/l)= max.300

Theoretical yield: 5 - 6 m² /lit.

Color shades: GraviHEL Color Tools

Distributed by: Crest Cormix Pty, Ltd. 13 Newmarket Lane,

Epping, Victoria 3076. Tel: +61 3 9945 2700 Fax: +61 3 9945 2799 Email: enquiries@crestcormix.com.au Web: www.crestcormix.com.au

HELIOS TBLUS, d.o.o., Količevo 65, 1230 Domžale, Slovenija T: +386 1 722 40 00, E: info@helios.si, www.helios.si



2:1 + 10-15% GraviHEL 2K PUR hardener GraviHEL thinner ESS Volume mixing Pot life / 20°C = 4h

 $\left| \left| \right\rangle \right|$



18 – 20 sec. DIN 53211 Φ 4mm/ 20°C

1,3 – 1,7 mm 2 - 3 bar (depending on type of gun) 1 -2x = 70 - 90 μm

Between coats: 10 min. /20°C

Powder dry/20°C =30 minutes Dry to touch/20°C = 5 h 60°C = 30 minutes



8 – 12 min. in the short-wave

0 - 10%



GraviHEL thinner ESS 0,23 – 0,33 mm 80 – 200 bar



Thinner is not needed!



Shelf life: 2 years

