

GRAVIHEL PUR TOPCOAT 602 MATT (PUR MAT- 602)

Use: High-quality two-component top coating for the protection of flat, veneered and massive furniture. The recommended ratio between the binder and the pastes is 80 : 20: If a superior hiding power is required, the quantity of pastes can be increased to a ratio of 75 : 25. All further information is provided based on the 80 : 20 ratio.

Surface:

GraviHEL PUR wood primer

Type of product:

2K alkyd - isocyanate

Appearance:

matt

Delivery viscosity:

Thixotropic

Density of component A:

1,098 – 1,196 kg/l

Solid Content:

By volume: 41%

By weight: 57%

VOC:

2004/42/IIIB(e)(840)540

VOC ready to use (g/l)= max.540

Theoretical yield:4 – 5 m²/lit.**Color shades:**

GraviHEL Color Tools

**2:1+ 25- 40%****GraviHEL 2K PUR wood hardener****GraviHEL 2K PUR wood thinner**

Volume mixing




18 – 20 sec.

DIN 53211 Φ 4mm/ 20°C

1,8 mm

2 bar

1x = 100 μ m

Between coats: 10 min. /20°C



Powder dry/20°C =10 minutes


Dry to touch/20°C = 15 – 30

0 - 10%

**GraviHEL 2K PUR wood thinner**

0,23 – 0,33 mm

80 – 200 bar



Shelf life:

2 years

Distributed by:

Crest Cormix Pty. Ltd.

13 Newmarket Lane,

Epping, Victoria 3076.

Tel: +61 3 9945 2700 Fax: +61 3 9945 2799

Email: enquiries@crestcormix.com.au

Web: www.crestcormix.com.au