

GRAVIHEL NITRO TOPCOAT 101 GLOSS (N - 101)

Use:

One-component quick-drying top coating based on nitrocellulose, used for the protection of wood and steel surfaces. The recommended ratio between the binder and the pastes is 85 : 15. If a superior hiding power is required, the quantity of pastes can be increased to a ratio of 80 : 20. All further information is provided based on the 85 : 15 ratio.

Surface:

GraviHEL alkyd primer RAL

Type of product:

Nitrocellulose

Appearance:

Gloss

Delivery viscosity:

Thixotropic

Density of component A:

1,001 – 1,094 kg/l

Solid Content:

By volume: 24%

By weight: 55%

VOC:

VOC ready to use (g/l)= max.710

Theoretical yield:

6 m²/lit.

Color shades:


GraviHEL Color Tools



80 – 100%
GraviHEL nitro thinner
20 – 22 sec.
DIN 53211 Φ 4 /20°C



1,3 mm
2 - 3 bar (depending on type of gun)
2x = 40 μ m



Between coats: 5-10 min. /20°C



Powder dry/20°C= 10 minutes
Dry to touch/20°C = 20 minutes



Shelf life:
2 years

Distributed by:
Crest Cormix Pty. Ltd.
13 Newmarket Lane,
Epping, Victoria 3076.

Tel: +61 3 9945 2700
Fax: +61 3 9945 2799
Email: enquiries@crestcormix.com.au
Web: www.crestcormix.com.au