

# MOBIHEL®

... for the cars we love

## ANTIGRAVEL LOW VOC

One component coating based on modified colofonium and caoutchuk for protection of sills and wheel arches against stone strokes.

It is resistant to salt, humidity, oil and benzine.

Possibility of over-coating immediately after drying.

**Distributed by:**

Crest Cormix Pty. Ltd.

13 Newmarket Lane,

Epping, Victoria 3076.

Tel: +61 3 9945 2700

Fax: +61 3 9945 2799

Email: [enquiries@crestcormix.com.au](mailto:enquiries@crestcormix.com.au)

Web: [www.crestcormix.com.au](http://www.crestcormix.com.au)

HELIOS TBLUS, d.o.o., Količevo 65, 1230 Domžale, Slovenija

T: +386 1 722 40 00, E: [office@helios-refinish.com](mailto:office@helios-refinish.com), [www.mobihel-refinish.com](http://www.mobihel-refinish.com)



<b>PACKING DATA</b>	<b>Packing:</b> 6 x 1.0 kg 6 x 1.0 kg	<b>Index:</b> 47056102 – grey 47056202 - black
<b>HYGIENE &amp; PERSONAL PROTECTION</b>		
<b>TECHNICAL CHARACTERISTICS</b>	<b>Colour:</b> <b>Product type:</b> <b>Density:</b>	Grey and black Synthetic resins free of asphalt or bitumen 1,500 – 1,508 g/l
<b>SUBSTRATE</b>	 Steel sheet metal	
<b>SUBSTRATE PREPARATION</b>	Substrates must be cleaned with MOBIHEL ANTISILICONE CLEANER prior to application.	
<b>PRODUCT PREPARATION/MIXING</b>		<b>Shake</b> 40x
<b>APPLICATION</b>	 	<b>Application with spray gun:</b> 3 - 5 bar 2 – 3x  <b>Temperature application</b> min. 15°C
<b>DRYING</b>		<b>Drying time at 20°C:</b> 60 – 90 min <b>Drying time at 60°C:</b> 30 min
<b>SHELF LIFE</b>		<b>Shelf life:</b> 2 years
<b>SAFETY ADVICE</b>	Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Avoid breathing dust/fume/gas/mist/vapours/spray. Avoid release to the environment. IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. If skin irritation occurs: Get medical advice/attention. In case of fire: use powder, foam or CO2 for extinction. <b>ONLY FOR PROFESSIONAL USE</b>	

