

... for the cars we love



PE PUTTY FIN

Two-component polyester fine levelling out mass to even out smaller irregularities after the sealer application (holes, scratches etc.).

Distributed by:

Crest Cormix Pty. Ltd.
13 Newmarket Lane,
Epping, Victoria 3076.
Tel: +61 3 9945 2700
Fax: +61 3 9945 2799
Email: enquiries@crestcormix.com.au

Email: enquiries@crestcormix.com.au
Web: www.crestcormix.com.au

HELIOS TBLUS, d.o.o., Količevo 65, 1230 Domžale, Slovenija

T: +386 1 722 40 00, E: office@helios-refinish.com, www.mobihel-refinish.com





PACKING DATA

Packing: 12 x 1.0 kg Index: 40786932

HYGIENE &
PERSONAL
PROTECTION











TECHNIC	AL
CHARACT	TERISTICS

	MOBIHEL PE PUTTY FINI	HARDENER	
Colour:	Light grey	Red	_7-,1
Product type:	Polyester resin	Peroxide	16-1-1
Density:	1,799 kg/l	1,2 kg/l	



2004/42/II B(a) (780) 720

EU limit value VOC for this type of products (category II B (a)) in the form, which is ready for application is 250 g/l VOC of this product, prepared for use is 170 g/l.

SUBSTRATE

it is always applied only to a suitably prepared filler

Mixing ratio:

100 g MOBIHEL PE PUTTY FINI 2 g BP Hardener

PRODUCT PREPARATION/MIXING



100

Pot life of the mixture at 20°:

7 - 10 min/20°C



Stir well

ADDI ICATION



Spreading

DRYING



Drying time at 20°C:

20 - 30 min



Drying time (infra-red short-wave):

5 min

Distance to the object: 70 - 80 cm

SANDING



Dry sanding:

P360 - P400



Wet sanding:

P600 - P800

FURTHER TREATMENT



Further treatment:

All 2K fillers from MOBIHEL program All topcoat from MOBIHEL program

SHELF LIFE



Shelf life:

18 months

SAEETV ADVICE

Obtain special instructions before use. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Do not breathe dust/fume/gas/mist/vapours/spray. IF exposed or concerned: Get medical advice/attention. If skin irritation occurs: Get medical advice/attention. In case of fire: use powder, foam or CO2 for extinction.

ONLY FOR PROFESSIONAL USE

Version: 8-16

